



# EUCON MRX

## MID-RANGE WATER-REDUCING ADMIXTURE

### DESCRIPTION

**EUCON MRX** is a specially formulated mid-range water-reducing and plasticizing admixture formulated using advanced dispersant technologies, specifically engineered for a wide-range of dosage rates without causing excessive retardation. Eucon MRX shows improved finishing characteristics when compared to other commonly used Type A and Type F water reducing admixtures. Eucon MRX can be used to reduce the total cement content and used in combination with supplementary cementitious materials (SCMs). Eucon MRX does not contain added chlorides or chemicals known to promote the corrosion of steel.

### PRIMARY APPLICATIONS

- Flatwork concrete
- Architectural concrete
- General purpose ready-mix concrete
- Concrete containing fly ash and other pozzolans
- Hot weather concreting

### FEATURES/BENEFITS

- Produces concrete with lower water to cement ratio allowing for increased strength
- Increased concrete strength lowers the potential for cracks
- Neutral effects on setting-times over a wide dosage range
- Improved workability aids in concrete placement and reduces labor cost
- Lower W/C allows for lower cement content/ ability to use SCMs, saving the producer money



### TECHNICAL INFORMATION

#### Performance Data

The following results were developed under laboratory conditions:

#### Mix Design

Cement T-I/II 600 lbs/yd<sup>3</sup> (272 kg/m<sup>3</sup>)  
 Stone 1800 lbs/yd<sup>3</sup> (1067 kg/m<sup>3</sup>)  
 Sand 1414 lbs/yd<sup>3</sup> (839 kg/m<sup>3</sup>)  
 W/C 0.49



## PACKAGING

Eucon MRX is available in bulk, 275 gal (1041L) totes, 55 gal (208 L) drums, and 5 gal (18.9 L) pails.

## SHELF LIFE

1 year in original, unopened container.

## SPECIFICATIONS/COMPLIANCES

Eucon MRX admixture meets requirements of ASTM C494/C494M and AASHTO M-194 as Type A & F admixtures.

## DIRECTIONS FOR USE

Eucon MRX can be added to the initial batch water or directly on the freshly batched concrete and mixed for approximately 5 minutes or 70 revolutions. However, better results have been observed batching directly on the freshly batched concrete. It should not come into contact with dry cement or other admixtures until mixed thoroughly with the concrete batch. Eucon MRX is dispensed with automatic equipment, thus insuring uniformity of admixture use throughout the project.


**Dosage Rates:** The recommended dosage rate for Eucon MRX is 3-12 oz/100lbs (195 to 782 mL/100 kg) of total cementitious materials.

**ASTM C 494 Type A:** Eucon MRX will typically achieve ASTM C494 Type A performance at 3-5 fl oz (196 to 325 mL/100 kg) per 100 lbs of cementitious.

Mid-Range performance: Eucon MRX is usually used at the rate of 5 to 7 fl oz (326 to 522 mL/100 kg) per 100 lbs of cementitious.

**ASTM C 494 Type F:** Eucon MRX can be typically used at a rate of 7 to 12 fl oz (522 to 782 mL/100 kg) per 100 lbs of cement for high-range admixture performance.

**Admixture Compatibility:** Eucon MRX is compatible with most admixtures including air-entraining agents, accelerators, most water-reducers, retarders, shrinkage reducers, corrosion inhibitors, viscosity modifiers, and microsilica; however, each material should be added to the concrete separately.



## PRECAUTIONS / LIMITATIONS

- Care should be taken to maintain Eucon MRX above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated.
- Do not agitate with air.
- Add to concrete mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.